AN - 1980-72231C [41]
A - [001] 011 04- 040 066 067 074 081 231 244 245 251 318 324 392 397 431
434 436 443 47& 477 57- 575 596 656 688
- [002] 011 04- 040 066 067 074 081 231 244 245 251 318 324 392 397 431
434 436 443 47& 477 57- 575 596 656 688
- [003] 011 04- 040 066 067 074 081 231 244 245 251 318 324 392 397 431
434 436 443 47& 477 57- 575 596 656 688
CPY - MERO-N
- NIKN
- NIKN
DC - A82 G02 L02 M13
FS - CPI
IC - C09D1/08 ; C09D5/08
KS - 0218 0231 0486 0787 1983 2007 2276 2335 2424 2430 2437 2439 2504 2654
2726 2728 2794
MC - A07-B A12-R01 G02-A05E L02-D07 L02-D14 M14-K
PA - (MERO-N) MEROCK SLURRY KAGAKU KK
- (NIKN) NIPPON KOKAN KK
- (NIKN) NIPPON KOKAN KOJI KK
PN - JP55110169 A 19800825 DW198041 000pp
- JP57039661B B 19820823 DW198237 000pp
PR - JP19790016215 19790216
XIC - C09D-001/08 ; C09D-005/08
AB - J55110169 Compsn. contains 100 pts.wt. Portland cement; 30-400 pts wt.
blast furnace slag which passes through a 0.85 mm sieve and 85% wt. of
slag does not pass through 0.25 mm sieve; and 5-40 pts.wt. (per 100
pts. of the total wt. of the Portland cement and blast furnace slag)
of an aq. emulsion of an organic polymer.
- Compsn. contains silica sand of 0.85-0.1 mm in particle dia. The aq.
emulsion is latex, asphalt, or acrylic, vinyl acetate or vinyl alcohol
series emulsion and may contain a non-ionic or cationic surfactant.
The compsn. is used for coating steel structures.
AW - POLYACRYLIC POLYVINYL ACETATE ALCOHOL PVA
AKW - POLYACRYLIC POLYVINYL ACETATE ALCOHOL PVA
IW - CORROSION RESISTANCE COATING COMPOSITION CONTAIN PORTLAND CEMENT BLAST
FURNACE SLAG AQUEOUS ORGANIC POLYMER EMULSION
IKW - CORROSION RESISTANCE COATING COMPOSITION CONTAIN PORTLAND CEMENT BLAST
FURNACE SLAG AQUEOUS ORGANIC POLYMER EMULSION
NC - 001
OPD - 1979-02-16
ORD - 1980-08-25
PAW - (MERO-N) MEROCK SLURRY KAGAKU KK
- (NIKN) NIPPON KOKAN KK
- (NIKN) NIPPON KOKAN KOJI KK
TI - Corrosion resistant coating compsn. - contains Portland cement, blast
furnace slag and an aq, organic polymer emulsion